

CHARACTERISTICS:

Food Approved Factor 1 according to E.E.C
Minimum Pigment Transfer
Exceptional Clarity, Stiffness and Strength

APPLICATIONS:

Food (Direct Contact), Commercial/Decorative and Candles (Including Scented), Business Forms, Boxes, Picture Frames.
Toys, Video Cassettes, Greeting Cards, Low Profile Paper Products, Envelopes, Notepads, Magazines and many more

STANDARD DIMENSIONS:

Thickness	Length [m]		Width [mm]
	Flat	Centerfolded	
S60	1,200	600	Min 100mm – Max 1200mm In 50mm increments as standard In 10mm increments as special order
H45	900	450	
XH30	600	300	
SXH225	550	225	

Core internal Diameter 76 mm

Other specifications available upon request

PROPERTIES	UNITS	THICKNESS			
		S60	H45	XH30	SXH225
YEILD	M ² / Kg	40.48	30.77	25.64	20.24
TENSILE STRENGTH	Kg/Cm ²	580—980			
ELONGATION	%	90—170			
INTERNAL TEAR RESISTANCE	Gr	5—14			
LIMIT OF ELASTICITY	Kg/Cm ²	5000—7200			
IMPACT STRENGTH	Gr	4.5—12			

THERMAL PROPERTIES		S60	H45	XH30	SXH225
SHRINKAGE AT 120°C					
	MD	>45			
	TD	>45			
SHRINKAGE STRESS	Kg/Cm ²	FIGURES NOT AVAILABLE			
SEALING STRENGTH	Kg/Cm ²	FIGURES NOT AVAILABLE			
SEALING TEMPERATURE	°F	250—320			
	°C	120—150			
SLIP COEFFICIENT		<0.25			

Dan Packaging Ltd T/A Get Me Packaging
Unit J, Coney Green Network Centre
Wingfield View, Clay Cross
Chesterfield
Derbyshire. S45 9HX

Tel: 01246 488999

Email: Sales@getmepackaging.co.uk

Website: www.getmepackaging.co.uk

Signed: 

Print Name: Mr Steve Holt

Position: Managing Director