

Tecbond 140

Version: Tecbond 140-TDS
 Date of last issue: 15/07/2025
 Date of first issue: 7/7/2015

General description

Tecbond 140 is an economical general-purpose adhesive suitable for use on wood, ceramics and some plastics.

Substrates*

- Paper
- Cardboard
- Wood
- Plastic (not PP or PE)
- Ceramics

Technical characteristics

Adhesive type: Synthetic polymer based hotmelt

Colour: Pale amber

Molten tack: High

Bulk Format: None

	12mm / ½"	15mm / ⅝"	43mm / 1¾"	Bulk
Carton QTY	5kg / 11lb	5kg / 11lb	10kg / 22lb	N/A
Suggested application temperature	195°C / 380°F	195°C / 380°F	195°C / 380°F	N/A
Brookfield viscosity @180°C (POW-12-VISC) spindle 27	6500cps	6500cps	4900cps	N/A
Ring & ball softening point (ASTM E28)	90°C / 197°F	90°C / 197°F	87°C / 189°F	N/A
Heat resistance (BS5350 Part H3)	75°C / 167°F	75°C / 167°F	75°C / 167°F	N/A
Open time	30 secs	30 secs	30 secs	N/A
Brittle point	10°C / 50°F	10°C / 50°F	0°C / 32°F	N/A

Storage

Store in a clean dry place at temperatures between 5°C / 41°F and 30°C / 86°F with boxes closed. Do not expose to direct sunlight or localised heat sources such as radiators or hot pipes.

Shelf life

Manufacturer guarantees 5-year shelf life after date of manufacture in accordance with suitable storage conditions as mentioned above.

Methods of application

Bead Adhesive Applicator.

Removal of adhesive

Assembled components can be separated by heating assembly to a temperature slightly above the heat resistance figure.

EVA & Polypropylene: Residues of EVA and polypropylene based hotmelts can be removed from components with white spirit.

Polyamide: Residues of polyamide based hotmelt can be removed from components with acetone

Disclaimer

The information contained on this data sheet is for guidance only. It is the result of careful laboratory evaluations by trained and qualified staff using British Standard or similar test methods. However, no warranty is expressed or implied regarding the accuracy of the data or the suitability of the adhesive for any specific purpose. In every case, we strongly recommend that the user shall make their own test to determine to their own satisfaction the suitability of the adhesive for their particular purpose. Neither the seller nor manufacturer shall be liable for any injury, loss, damage, direct or consequential arising out of the use or inability to use the product. Further information is always available to help solve your adhesive problems. Should you require any further information on our adhesives please contact your nearest distributor.

*In every case, we strongly recommend that the user shall make their own test to determine to their own satisfaction the suitability of the adhesive for their particular purpose.

F.D.A. approved. All the constituent parts of this adhesive have been approved by the American F.D.A. under C.F.R. 21.175.105 (adhesives) (subject to limitations).